Type
An auxiliary drier based on Calcium octoate

Features
- Auxiliary drier that is used solely in combination with primary and secondary driers
- Yields synergistic effects in combination with primary driers such as cobalt, and with secondary driers such as zirconium
- Can be used as a pigment wetting agent and loss-of-dry additive
- Prevents adsorption of primary driers by the pigments thereby stabilizing surface dry

Usage
Oxidatively cured solvent-based systems, including:
- Architectural paints
- Industrial coatings
- stains

Typical Properties

Metal content	%Ca	10±0.5
Solid content	(%)	77-85
Density	(g/ml)	0.9±0.1
Viscosity*	(s)	Max 110
Color	(Gardner)	Max 6
Solvent	-	White spirit

*Table 1 - * Viscosity measured by Cup 6 [250C]*

Packing
Package size: 180 Kg
Shelf life: 18 months

Storage
The product should be kept in dry and cool (t<30°C) condition away from sources of heat, spark and sun light.
The product should not be unsealed unless for consumption.

Health and Safety
- Avoid skin and eye contact by wearing overalls, gloves, goggles and masks
- Use the drier under well-ventilated condition
- Remove the spillage by thorough washing